

# Product Data Sheet

No. 10275 - 11/20

## SPEED E-NAMEL™

AEROSOL CARB MIR: <0.80 FLAT, <0.95 NON FLAT, <1.25 METALLIC

PRODUCT NUMBERS:	Z275 SEMI-GLOSS WHITE	Z357 CHOCOLATE BROWN	Z469 HUNTER GREEN	Z516 PURPLE
	Z277 SEMI-GLOSS BLACK	Z377 FLAT WHITE	Z470 BERMUDA BLUE	Z517 RICH RED
	Z297 PERSIMMON	Z387 GLOSS BLACK	Z471 ROYAL BLUE	Z518 PINK
	Z298 ORANGE	Z397 GLOSS WHITE	Z482 ALMOND	Z519 BURGUNDY
	Z307 ACRYLIC CLEAR	Z407 GOLD	Z487 FLAT BLACK	Z525 KELLY GREEN
	Z308 SILVER	Z467 LEMON YELLOW	Z489 LIGHT GRAY	Z813 RED
	Z317 ALUMINUM	Z468 MEDIUM GRAY	Z506 ANTIQUE WHITE	

### I. GENERAL DESCRIPTION

**Description:** The *Fast-Dry Quality Finish* that flies off the shelf! This all purpose enamel coating is formulated for interior and exterior use on a variety of surfaces. A superior quality, tough, durable finish that prevents rust and dries in minutes.

**Benefits:** Zynolyte® Speed E-NameL™ provides excellent adhesion to all metal, wood and masonry surfaces. Good gloss and hide coverage. Protects metal and wood surfaces from rust and corrosion. Dry to the touch in 15 minutes. Get a smooth, professional finish every time.

**Application:** Great for furniture, metal and wood railings, fences, bicycles, hobbies, crafts, plastic and metal garden accessories, cabinets, doors, patio items, wicker, tools masonry, bulkheads, and much more. Can be used indoors or outdoors.

**Directions:** Surface should be clean, dry and free of all dust dirt, grease, wax, mildew, or other contaminants that would adversely affect paint adhesion. On bare metal or lightly rusted surfaces, Zynolyte® Multi-Purpose Primer is recommended prior to finish color application. Extremely slick, glossy surfaces should be lightly sanded. Wipe surface with tack cloth to remove debris. Cover adjacent areas to protect from spray mist. For best results, use at temperatures between 60°F and 80°F (16°C and 27°C). Use in a well ventilated area. Shake can for at least one minute after rattle of agitator ball is heard, and intermittently during use. Hold can 10-12 inches from surface to be coated, and press sprayhead firmly. Use steady, even strokes while spraying. Two light coats are better than one heavy coat. Wait one to two minutes before recoat. After spraying, turn can upside down and press spray button for approximately two seconds to clear paint in valve.

**Limitations:** Please refer to the Safety Data Sheet for specific information on material hazards, etc.

#### Packaging:

Aerosol:	Cans (16 oz.) 12/case	11 oz. net wt. (312 grams) 7 lbs. (3.17 kg)	13.6 fl. oz. (366 ml) 0.44 CF (0.013 CM)
----------	--------------------------	--	---

---

## II. CHARACTERISTICS & PROPERTIES (Average for all colors)

---

### Specifications:

Complies with CARB MIR regulations.

### Appearance:

Gloss at 60° ..... Flat <5, Semi-Gloss 35-60, Gloss 90  
Class ..... Flat, Semi-Gloss, Gloss & Metallic

### Coverage:

Theoretical—at 1 mil dry ..... 13 sq. ft.  
Practical—at 1/2 mil dry ..... 26 sq. ft.

### Drying Schedule: (At 77°F [25°C], 50% Humidity at 1 mil, dry)

To touch ..... 15 minutes  
To handle ..... 30 minutes  
Full cure ..... 72 hours  
To recoat ..... Before 2 hours or after 72 hours

### Performance and Chemical Properties:

Weight per gallon ..... 5.98  
Specific gravity ..... 0.72  
Viscosity ..... Not applicable  
Flammability: Label marking ..... Extremely flammable  
Flash point ..... <0°F (-18°C)  
Operating temperature range ..... 60°- 80°F (16° - 27°C)  
Percent solids by weight ..... 14%  
Percent solids by volume ..... 8%  
Percent pigment by volume ..... 1%  
CARB MIR (Flat, Non-flat, Metallic) ..... <0.80, <0.95, <1.25  
Interior durability ..... Excellent  
Exterior durability ..... Excellent  
Temperature resistance ..... 200°F (93°C)  
Color fastness ..... Excellent  
Adhesion ..... Excellent over properly prepared surface  
Salt spray corrosion ..... 200 hours  
Mineral spirits resistance ..... Good  
Gasoline resistance ..... Poor  
Motor oil resistance ..... Good  
Pencil hardness ..... H

### Base Materials:

Resin system ..... Acrylic VT alkyd  
Solvents (top two) ..... Acetone, VM&P Naphtha  
Propellent system ..... Hydrocarbon

---

## III. SHIPPING, STORAGE AND HEALTH

---

UN number ..... UN1950  
Proper Shipping Description ..... Aerosols  
Hazard Class ..... 2.1  
Packing Group ..... N/A  
Limited Quantity ..... Yes  
Warehouse storage level number ..... NFPA 30B Level 3  
Storage temperature ..... 50° to 120°F (10° to 49°C)  
Shelf life ..... 1 to 2 years

### HMIS ratings

Health ..... 2  
Fire ..... 4  
Reactivity ..... 1

---

## IV. MISCELLANEOUS

---

Contains no Ozone Depleting Substances (O.D.S.)

---

## V. WARRANTY

---

1-year warranty to the original registered owner on all products from date of purchase. User returns, exchanges and defective refunds must be made with the original place of purchase. Because Aervoe cannot control Buyer's handling or use of product, Aervoe makes no warranty expressed or implied when not used or stored in accordance with directions. Aervoe shall not be liable for cost of labor, incidental or consequential damages, and this warranty is limited to replacement or repair of product or credit of purchase.